



# White Horse Reference Materials

## Certificate of Analysis

### WHRM-Tja (Lot a)

**ISSUE (MFG) DATE:** JULY 1, 2017

**REVISION DATE:** 04/27/2026

#### H<sub>2</sub> IN TITANIUM ALLOY

**INTENDED USE:** This Certified Reference Material (CRM) is intended primarily for use as a calibrant for calibrating instruments used to determine the listed elemental content(s) in refractory alloys. In addition, it can be used to check instrumental performance and harmonization among laboratories.

**DESCRIPTION:** One bottle consists of ~100 Titanium pins of approximately 2 mm diameter by 4 mm length with a nominal weight of 0.12 g.

#### Mass Fraction % Expanded Uncertainty U=95 %

<b>Hydrogen (H)</b>	<b>0.0131</b>	<b>± 0.00033</b>
---------------------	---------------	------------------

**VALUE ASSESSMENT:** The measurand listed is the amount of the element contained in Titanium traceable to the derived SI unit of mass fraction expressed as WT%.

Test result is realized using inert gas fusion method WHRM ME1447a.

This method employs gas dose spiking and calibration at WHRM.

For propagation of uncertainty, an estimate of the combined standard uncertainty can be obtained as  $u_c = U95\%(x)/k$ , where  $k = 2$  is the approximate coverage factor associated with the 95 % coverage level. The resulting value for  $u_c$  is at the level of one standard deviation, and it can be combined with a laboratory's standard uncertainty estimates for their own sources of error to calculate estimates of uncertainty for test results from methods with which this CRM was used. A laboratory uncertainty estimate that includes the uncertainty of the CRM value is the basis for a link of metrological traceability from the test result for a sample to the CRM value. In addition, the value of  $u_c$  can be used as an estimate of  $\hat{\sigma}$  or  $u_{av}$  in proficiency testing according to ISO 17043:2023.

**MINIMUM SAMPLE QUANTITY:** To relate analytical determinations of Hydrogen to the assigned value on this COA, an unknown sample mass for hydrogen analyses should ideally be ~0.225g with 2 pellets of tin flux.

**HETEROGENEITY** Material heterogeneity was low and fit for purpose for value assignment. Heterogeneity testing was performed at WHRM using inert gas fusion with thermal conductivity detection using a LECO hydrogen analyzer following ASTM E1447. ANOVA demonstrates that bottle-to-bottle variance is indistinguishable from the overall standard deviation calculated from of 50 sample analyses (selected from 10 bottles for 5 repetitions.)

**PERIOD OF VALIDITY:** The listed value assignment(s) are valid, within the measurement uncertainty specified, indefinitely, provided the CRM is handled and stored in accordance with the instructions given in this document (see "Instructions for Handling and Use").

**STORAGE INSTRUCTIONS:** The material should be stored in its original, tightly capped bottle in a cool, dry location.

**INSTRUCTIONS FOR HANDLING AND USE:** The material does not require additional preparation prior to weighing, if stored as outlined per instructions given in this document (see “Storage Information”). Use a clean, dry tool to handle the pins, and do not touch the pins with any material likely to contaminate the surface.

**MAINTENANCE OF RM DOCUMENT:** WHRM will monitor this CRM over the period of validity. If substantive technical changes affect the value assignment, WHRM will publish on its website the revised document, and the purchaser via the information available on the included registration form (see attached sheet or register online). Users of this CRM should ensure the COA in their possession is current.

**PREPARATION AND ANALYSIS:** The material for WHRM-THA was obtained in the form of pins prepared by White Horse Technical Services (WHTS) using a proprietary process. The material was blended and bottled at WHTS. The starting material for preparation of WHRM-TJA was a Titanium alloy.

Quantitative analysis of the listed elemental content of the material [single-heat (lot)] for WHRM-TJA was performed at WHRM using inert gas fusion with thermal conductivity detection for H2.

**QUALITY ASSURANCE:** For quality assurance, various CRMs were analyzed by WHRM at the same time as blunder checks and showed no statistically significant bias.

WHRM certifies that TJA was produced and is maintained in a manner compliant with the requirements of ISO 17034 and associated documents. WHRM remains committed to a responsible adherence to best practices as developed and demonstrated in both public and private sector organizations and as set forth in international Reference Material Producer requirements.

**HEALTH AND SAFETY INFORMATION:** This product is Non-Hazardous in solid form.

**STATISTICAL ANALYST:**   
**Curtis Vancura, Owner WHRM**

Legal Notice: Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall WHTS be liable for incidental or consequential damages. For good laboratory practice it is recommended that all standards be verified prior to use.